



Velvet Textured Polycarbonate Overlaminating Film 7737FL • 7738FL

Technical Data

August 2013

Product Description 3M™ Velvet Textured Polycarbonate Overlaminating Films 7737FL and 7738FL utilize velvet textured polycarbonate film to achieve a decorative velvet appearance. 3M™ Adhesive 400 offers excellent low temperature performance and long term aging for resistance to yellowing in outdoor applications.

Construction

Product Number	Adhesive	Liner
3M overlaminating film 7737FL	#400 Acrylic 0.8 mil (20 micron)	.0015 in. Clear Polyester Liner (38 micron)
3M overlaminating film 7738FL	#400 Acrylic 0.8 mil (20 micron)	.0015 in. Clear Polyester Liner (38 micron)

(Calipers are nominal values.)

Features

- Velvet textured polycarbonate overlamine offers the opportunity to achieve the attractive appearance of a subsurface screen printed nameplate with an economical overlamine construction which can create looks that are unique.
- Film liner offers superior graphic appearance when overlaminating metallized or darker surfaces.
- UL recognized (File MH11410) for overlamination of polyester labelstocks.
- CSA Accepted (File 99316) for overlamination of both polyester and vinyl labelstocks.

Application Ideas

- Decorative, protective overlamine on pressure sensitive labels and tags.
- Overlamine on appliques and decorative trim strips.
- Economical method of achieving the look of a velvet textured nameplate – recommend 3M™ Printable Polyesters as a basestock.

3M™ Velvet Textured Polycarbonate Overlaminating Film

7737FL • 7738FL

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Coat Weight	1.05 to 1.65 g/100 in. ²	TM-2279
Release Range	5 to 55 g/2 in.	TLMI Method, 180° removal, 300 in./min.
Service Temperature	-40°F to 250°F (-40°C to 121°C)	
Minimum Application Temperature	10°F (-12°C)	
Convertability	Low temperature, high clarity 3M™ Acrylic Adhesive 400 is specifically designed to be compatible with a variety of print methods and overlaminate applications. When converting labels for thermal transfer applications, care should be taken with regard to proper roll tensions, handling and storage conditions. Please refer to the die cutting/converting section of this data page or the "Guide to Converting and Handling Label Products" technical bulletin for additional information.	

Typical Peel Adhesion Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Peel test procedure is ASTM D-3330

	Initial (10 Minute Dwell/RT)	
	180° Peel	
Surface	oz/in	N/100 mm
Stainless Steel	38	42

Environmental Performance

Samples were applied to stainless steel panels and allowed to dwell for 24 hours prior to exposures.

Liquid	Dwell Time/Exposure Condition	Results
Isopropyl Alcohol @ Room Temperature	4 hours	Good appearance – 1/16" edge penetration
5% Sulfuric Acid @ Room Temperature	4 hours	Good appearance – no edge penetration
Engine Oil @ 250°F (121°C)	4 hours	Good appearance – no edge penetration
Water @ Room Temperature	24 hours	Good appearance – no edge penetration

Temperature Resistance:

-40°F (-40°C) to 250°F (121°C) for 1 day: no change

Humidity Resistance:

1 day at 95°F (35°C) and 95% relative humidity: no change

3M™ Velvet Textured Polycarbonate Overlaminating Film

7737FL • 7738FL

Application Techniques For maximum bond strength, the surface should be clean and dry. A typical cleaning solvent is heptane or isopropyl alcohol.*

For best bonding conditions, application surfaces should be at room temperature or slightly higher. Low temperature surfaces, below 50°F (10°C), cause the adhesive to become firm and will not allow the adhesive to flow and develop intimate contact with the substrate.

***Note:** When using solvents, read and follow the manufacturer's precautions and directions for use.

Printing This film is not treated for printability.

Storage Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Shelf Life If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.

Technical Information The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2008

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2008 standards.

3M

**Industrial Adhesives and Tapes Division
Converter Markets**

1030 Lake Road
Medina, OH 44256-0428
800-422-8116 • 877-722-5072 (fax)
www.3M.com/converter



*Recycled Paper
40% pre-consumer
10% post-consumer*

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2011 70070275782 (12/11)